




























# Understanding Superior Service



## 29- AND 26-GAUGE

			
POLAR WHITE SR .60 SRI 71	LIGHT STONE SR .50 SRI 57	ASH GRAY SR .47 SRI 55	SADDLE TAN SR .48 SRI 55
			
BURNISHED SLATE SR .28 SRI 27	RUSTIC RED SR .36 SRI 38	EVERGREEN SR .34 SRI 35	IVY GREEN SR .28 SRI 27
			
BERRY SR .30 SRI 27	COCOA BROWN SR .28 SRI 27	CHARCOAL GRAY SR .27 SRI 26	CRIMSON RED SR .33 SRI 34
			
HAWAIIAN BLUE SR .32 SRI 32	BLACK SR .30 SRI 30	DESERT SAND SR .42 SRI 47	ANTIQUE BRONZE* SR .26 SRI 25
			
OLD TOWN GRAY SR .42 SRI 47	GALLERY BLUE SR .27 SRI 26	FERN GREEN SR .27 SRI 26	IVORY SR .65 SRI 78
			
COPPER METALLIC SR .45 SRI 50	TAUPE* SR .38 SRI 41	BUCKSKIN* SR .34 SRI 35	COLONY GREEN SR .31 SRI 32
			
DARK RED* SR .26 SRI 25	BRIGHT WHITE* SR .71 SRI 86	GALVALUME	

- Final color selection should be made from actual color chips.
- Visit [www.unitedsteelsupply.com](http://www.unitedsteelsupply.com) for the most current information.
- A 40-year limited paint warranty is available for all colors upon written request. Please inquire. (Outside the continental United States, please inquire.)
- Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a material's ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance. ENERGY STAR requires an SR value of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit [www.energystar.gov](http://www.energystar.gov).
- Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit [www.usgbc.org](http://www.usgbc.org).

PROUDLY FINISHED WITH  
**SHERWIN-WILLIAMS**  
Coil Coatings



\*AVAILABLE IN 29GA ONLY

UNITED STEEL SUPPLY

Standard Color OFFERINGS