



STANDARD COLOR OFFERINGS

Artic White SR .69 SRI 84	Polar White SR .64 SRI 77	Bone White SR .61 SRI 72	Ivory SR .69 SRI 84	Light Stone SR .56 SRI 65
Saddle Tan SR .47 SRI 53	Desert Sand SR .42 SRI 47	Taupe SR .38 SRI 41	Buckskin SR .33 SRI 34	Burnished Slate SR .34 SRI 35
Antique Bronze SR .24 SRI 22	Light Brown SR .38 SRI 41	Koko Brown SR .35 SRI 37	Brown SR .33 SRI 34	Black SR .31 SRI 31
Ash Gray SR .46 SRI 52	Old Town Gray SR .41 SRI 45	Charcoal Gray SR .37 SRI 31	Charcoal Gray II SR .35 SRI 37	Charcoal Blue Gray SR .29 SRI 29
Rustic Red SR .36 SRI 38	Rural Red SR .34 SRI 35	Dark Red SR .36 SRI 39	Crimson Red SR .31 SRI 31	Berry SR .29 SRI 29
Evergreen SR .35 SRI 37	Ivy Green SR .28 SRI 27	Fern Green SR .29 SRI 29	Colony Green SR .28 SRI 27	Hawaiian Blue SR .31 SRI 31
Gallery Blue SR .26 SRI 24				
Charcoal Gray CRINKLE SR .33 SRI 35	Black CRINKLE SR .29 SRI 29	Evergreen CRINKLE SR .33 SRI 35	Rustic Red CRINKLE SR .32 SRI 33	Burnished Slate CRINKLE SR .30 SRI 31
Koko Brown CRINKLE SR .33 SRI 34	Acrylic GALVALUME® N/A	Copper Metallic SR .51 SRI 58		



**STEEL PRODUCTS
FOR THE METAL
ROOFING AND METAL
BUILDING INDUSTRY**

- > Final color selection should be made from actual color chips.
- > For the most current information, visit unitedsteelsupply.com
- > A 40-Year limited paint warranty is available for all colors upon written request. Please inquire. *(Outside the continental United States, please inquire).*
- > Solar Reflectivity (SR): Solar reflectivity or reflectance is the measure of a materials ability to reflect solar energy or sunlight from its surface. SR values are numbered 0 to 1.0. A value of 0 indicates that the surface absorbs all solar energy and a value of 1.0 indicates total reflectance. ENERGY STAR requires an SR value of 0.25 or higher for steep slope roofing (above 2:12) and an SR value of 0.65 or higher for low slope roofing (2:12 or less). For more information, please visit energystar.gov.
- > Solar Reflectance Index (SRI): The SRI is used to determine compliance with LEED requirements and is calculated according to ASTM E 1980 using values for reflectance and emissivity. To meet LEED requirements, a roofing material must have an SRI of 29 or greater for steep slope roofing and an SRI value of 78 or higher for low slope roofing. For more information, visit usgbc.org.

PROUDLY FINISHED WITH
SHERWIN-WILLIAMS
Coil Coatings



Standard Color Offerings

Color Name	29ga 40.8750 GR80 AZ50	26ga 41.5625 GR80 AZ50	26ga 41.5625 GR50 AZ50	26ga 20-20.5 GR50 AZ50	26ga 43.0000 GR80 AZ50
Acrylic GALVALUME®	●	●	●	●	●
Antique Bronze	●	□	□	□	□
Artic White	●	□	●	○	●
Ash Gray	●	●	●	○	●
Burnished Slate	●	●	●	○	●
Berry	●	●	●	○	●
Black	●	●	●	○	●
Bone White	●	●	●	○	●
Brown	●	●	●	○	●
Buckskin	●	□	□	□	□
Charcoal Gray	●	●	●	○	●
Charcoal Gray II	●	□	●	○	●
Charcoal Blue Gray	●	□	●	○	●
Colony Green	●	□	●	○	●
Copper Metallic	●	●	●	○	●
Crimson Red	●	●	●	○	●
Dark Red	●	□	□	□	□
Desert Sand	●	●	●	○	●
Evergreen	●	●	●	○	●
Fern Green	●	●	●	○	●
Gallery Blue	●	●	●	○	●
Haw Blue	●	●	●	○	●
Ivory	●	●	●	○	●
Ivy Green	●	●	●	○	●
Koko Brown	●	●	●	○	●
Light Brown	●	●	●	○	□
Light Stone	●	●	●	○	●
Old Town Gray	●	●	●	○	●
Polar White	●	●	●	○	●
Rural Red	●	●	●	○	●
Rustic Red	●	●	●	○	●
Saddle Tan	●	●	●	○	●
Taupe	●	●	●	○	●
Black CRINKLE	●	□	●	○	□
Burnished Slate CRINKLE	●	□	●	○	□
Charcoal Gray CRINKLE	●	□	●	○	□
Evergreen CRINKLE	●	□	●	○	□
Koko Brown CRINKLE	●	□	●	○	□
Rustic Red CRINKLE	●	□	●	○	□

● = Stock Color/Width ○ = Stock Color, 1-3 day slitting lead time □ = Paint-to-order, minimum required